SUSTAINABLE PERFORMANCE COLOR CARD

 $\underset{\mathsf{T}}{\mathsf{M}} \underset{\mathsf{E}}{\mathsf{O}} \underset{\mathsf{X}}{\mathsf{M}} \underset{\mathsf{T}}{\mathsf{E}} \underset{\mathsf{I}}{\mathsf{N}} \underset{\mathsf{I}}{\mathsf{T}} \underset{\mathsf{L}}{\mathsf{U}} \underset{\mathsf{E}}{\mathsf{M}}$



solutions@krug.ca | www.krug.ca | 1.888.578.5784

SPECIFICATIONS

Width - Pattern	Fiber Content & Backing	Abrasion (D.R.)	Light- fastness	Approx. Repeats	Cleaning Code
57" INFINITY	74% Post Consumer Recycled Polyester, 26% Polyester Acrylic Backing	200,000	40 Hrs. Class 4	⅓" L, 5⁄8" W	WS
57" MARATHON	75% Post Consumer Recycled Polyester, 25% Polyester Acrylic Backing	200,000	40 Hrs. Class 4	1/8" L, 1/8" W	WS
56" MILLENNIUM	85% Post Consumer Recycled Polyester, 15% Polyester Acrylic Backing	200,000	40 Hrs. Class 4	1/8" L, 1/8" W	WS
56" ODYSSEY	67% Post Consumer Recycled Polyester, 33% Polyester Acrylic Backing	200,000	40 Hrs. Class 4	1/8" L, 1/8" W	WS
56" TRADITION	72% Post Consumer Recycled Polyester, 28% Polyester Acrylic Backing	200,000	40 Hrs. Class 4	1/8" L, 1/8" W	WS

*ACT® Registered Certification Marks

EXPLANATION OF **ACT** ICONS FOR UPHOLSTERY

EXI LANAHON OF ACT TOONS FOR OTHER			
FIRE RETARDANCY	Flammability testing determined as fabric's resistance to burning. PASSES California 117-2013		
COLORFASTNESS TO WET & DRY CROCKING	Colorfastness to wet & dry crocking refers to the rubbing off of color from the fabric onto clothing, hands or other materials a can occur under wet or dry conditions.		
	PASSES AATCC 8-1974 Dry Crocking, Class 4 minimum; Wet Crocking, Class 3 minimum		
COLORFASTNESS TO LIGHT	Colorfastness to light is the degree to which fabric will retain its color when exposed to light.		
*	PASSES AATCC 16A-1974 or AATCC 16E-1976; Class 4 minimum at 40 hours NOTE: Class 4 minimum at 60 hours is recommended for direct sunlight exposure situations		
PHYSICAL PROPERTIES	3 physical property tests include: brush pill test to determine a fabric's pilling. Breaking/tensile strength is the ability of a fabric to withstand tension without breaking or tearing. Seam slippage is the pulling apart of fabrics at the seams.		
A	PASSES Brush Pill ASTM D3511, 3-4 minimum Breaking Strength ASTM D3597-D1682-64 (1975) 50 lbs. minimum in warp & weft Seam Slippage ASTM D3597-D434-75 25 lbs. minimum in warp & weft		
ABRASION	Abrasion is the ability of a fabric to withstand damage from wear and rubbing. There is a general contract specification as well as a heavy duty specification.		
General Co.	PASSES ntract ASTM 3597 modified (#10 cotton duck); 15,000 double rubs Wyzenbeek Method		
A	<u>v Duty</u> ASTM 3597 modified (#10 cotton duck); 30,000 double rubs Wyzenbeek Method or ASTM D4966		

CLEANING CODE DEFINITIONS

WS: Water-based cleaning agents or foam

(with 21 oz. weight); 40,000 rubs Martindale Method



GREENGUARD
RODUCT CIRTINID FOR
Eligible for CHPS Low-Emitting Material Credits.



For memo samples please contact. $\underset{\mathsf{T}}{\mathsf{M}} \underset{\mathsf{E}}{\mathsf{O}} \underset{\mathsf{X}}{\mathsf{M}} \underset{\mathsf{T}}{\mathsf{E}} \underset{\mathsf{I}}{\mathsf{N}} \underset{\mathsf{I}}{\mathsf{T}} \underset{\mathsf{L}}{\mathsf{U}} \underset{\mathsf{E}}{\mathsf{M}}$ Canada 905-670-5002 Toll Free 800-366-6839



