

IMPRESSION

SPECIFICATIONS

ABRASION Exceeds 1,500,000 Double Rubs

ANTI-PINKING Passes ASTM 1428

CONTENT 100% Polyvinyl Chloride (PVC)

BACKING CONTENT 100% Polyester

CLEANING CODE Cleanable with Virox 5, Oxivir Plus, Oxivir TB, Oxivir TB

wipes, Accel Five TB, Accel PREVention, Accel PREVention wipes, Oasis 146 and bleach. Dilution ratios must be followed. Rinse the cleaned area after with fresh water

and wipe dry with a clean cloth.

COLD CRACK -55°C (-67°F)

COLORS 40 available

CROCKING AATCC 8: Dry = Class 5, Wet = Class 5

ELONGATION Passes ASTM D751: Weft 116%, Warp 64%

FIRE RETARDANCY* CALTB117-2013, IMO FTP Code 2010 - Part 8,

MVSS302, NFPA 260 Class 1, UFAC Class 1

ANTI-BACTERIAL Passes AATCC 147-2011

MILDEW RESISTANT Passes ASTM G21-13

PROTECTIVE FINISH Endurepel Armour

SEAM SLIPPAGE Passes ASTM D751: Weft = 64 lbs., Warp = 67 lbs.

TEAR STRENGTH Passes ASTM D2261: Weft = 13 lbs., Warp = 10 lbs,

Passes ASTM D751: Weft = 12 lbs., Warp = 10 lbs Passes ASTM D751: Weft = 94 lbs., Warp = 101 lbs

THICKNESS 1.10 mm

UV/LIGHTFASTNESS AATCC 16.3 - Grade 4.0 (1,500 hours)

WEIGHT 21.71 oz./yd2

33.17 oz./lin. yd

WIDTH 55" (140 cm)

ROLL SIZE 30 yd; 27 m

*This term and any corresponding data refer to typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions. This information is offered for your general guidance only. It's accurate to the best of our knowledge and is not intended to relieve the user from its responsibility to investigate and understand other pertinent sources of information and to comply with all laws and procedures applicable to the safe handling and use of this material. Final determination of the suitability of any product for an application rests with the user.

Impression is protected with a 3 year warranty.



TENSILE STRENGTH







IMPRESSION (GRADE 3)

