

## **PARAMOUNT**

## **SPECIFICATIONS**

**ABRASION** Exceeds 500,000 Double Rubs

**CLEANING CODE** Cleanable with Virox 5, Oxivir Plus, Oxivir TB, Oxivir TB wipes, Accel Five

TB, Accel PREVention, Accel PREVention wipes, Oasis 146 and bleach. Dilution ratios must be followed. Rinse the cleaned area after with

fresh water and wipe dry with a clean cloth.

**CONTENT** 100% Polyurethane

**CONTENT BACKING** 85% Polyester, 15% Cotton

**COLD CRACK** -32°C (-25°F)

**COLORS** 30 available

**CROCKING** AATCC 8: Dry = Class 5, Wet = Class 5

**ELONGATION** ASTM D751: Warp = 14.3%, Weft = 25.7%

FIRE RETARDANCY\* CAL117-2013; NFPA 260 Class 1; UFAC Class 1

**HYDROLYSIS** ASTM D3690-02 Sect. 6.11 (Hydrolytic Stability), ISO 1419 Method C

(Accelerated Aging) (Jungle Test) 10 Weeks

ANTI-BACTERIAL Yes

MILDEW RESISTANT Yes

**PROTECTIVE FINISH** Endurepel Armour

**SEAM SLIPPAGE** Passes ASTM D751: Warp = 149 lbs; Weft = 105 lbs

**TEAR STRENGTH**Passes ASTM D751: Warp = 3.1 kg/7.6 cm;

Weft = 1.9 kg/7.6 cm

**TENSILE STRENGTH** Passes ASTM D751: Warp = 38 lbs; Weft = 26 lbs

THICKNESS 0.95 mm

**UV/LIGHTFASTNESS** AATCC16 Class 5; 200 Hours

**WEIGHT** 13.45 Oz./yd2

20.17 Oz./lin. yd

**WIDTH** 54" (137 cm)

**ROLL SIZE** 40 yd; 36 m

<sup>\*</sup>This term and any corresponding data refer to typical performance in the specific tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions. This information is offered for your general guidance only. It's accurate to the best of our knowledge and is not intended to relieve the user from its responsibility to investigate and understand other pertinent sources of information and to comply with all laws and procedures applicable to the safe handling and use of this material. Final determination of the suitability of any product for an application rests with the user.





## PARAMOUNT (GRADE 4)

